

LOCTITE®



LOCTITE® 3D PRO476™

Tough
Black

LOCTITE®
Henkel Corporation
loctite3dp@henkel.com





PRO476™ TOUGH



LOCTITE 3D PRO476™

LOCTITE 3DP PRO476 is a high-strength photo-plastic with good impact resistance, moderate heat resistance and excellent surface finish.

LOCTIT 3D PRO476 is ideal for a variety of performance prototype and tooling applications and can be machined, tapped, or polished for final finish..

LOCTITE 3D PRO476 is formulated to print optimally on LCD printers on a wavelength of 405nm.



Benefits:

- Tough
- High impact resistance
- Moderate heat resistance, HDT 60°C
- Excellent surface finish



Ideal for:

- Textured and highly detailed parts
- Performance prototypes
- Jigs, fixtures & manufacturing aids
- Housing and covers



Markets:



Industry



Automotive



Consumer Goods



LOCTITE®

PRO476™ TOUGH BLACK



PROPERTIES

Mechanical Properties	Measure	Method	Green	Post Processed
Young's Modulus	MPa	ASTM D638	1000 ^[4] – 1350 ^[3]	1550 ^[6] – 1730 ^[5]
Tensile Stress at Yield	MPa	ASTM D638	28 ^[4] – 33 ^[3]	42 ^[6] – 43 ^[5]
Elongation at Yield	MPa	ASTM D638	5.1 ^[4] – 5.3 ^[3]	4.3 ^[6] – 5.2 ^[5]
Tensile Stress at Break	MPa	ASTM D638	29 ^[4] – 32 ^[3]	39 ^[5] – 42 ^[6]
Elongation at Break	%	ASTM D638	70 ^[3] – 75 ^[4]	55 ^[6] – 60 ^[5]
Flexural Modulus	MPa	ASTM D790	-	1850 ^[8] – 2000 ^[7]
Flexural Strain at Break	%	ASTM D790	-	>5 ^[7,8]
IZOD Impact (Notched)	J/m	ASTM D256	-	40 – 45 ^[11]
Shore Hardness (3s)	D	ASTM D2240	-	77 – 79 ^[13]
Other Properties				
HDT at 0.455 MPa	°C	ASTM D648	-	60 ^[9] – 62 ^[10]
HDT at 1.82 MPa	°C	ASTM D648	-	43 – 47 ^[10]
Water Absorption (24hr)	%	ASTM D570	-	2.1 ^[12] – 2.4 ^[15]
Water Absorption (48hr)	%	ASTM D570	-	2.8 – 2.9 ^[12]
Water Absorption (72hr)	%	ASTM D570	-	3.3 ^[12] – 3.8 ^[15]
Solid Density	g/cm ³	ASTM D792	-	1.11 – 1.31 ^[14]
Liquid Properties				
Viscosity @ 25°C (77°F)	cP	ASTM D7867	-	612 ^[1.1] – 832 ^[1]
Liquid Density	g/cm ³	ASTM D1475	-	1.08 ^[2]

Test parameters:

All specimen are printed unless otherwise noted. All specimen were in ambient lab conditions at 19-23°C / 40-60% RH for at least 24 hours. ASTM Methods: D638 Type IV, 5mm/min; D790-B 1.3 mm/min; D256 Notched IZOD (Machine Notched) 6 mm x 12 mm; D2240 Type "D" (3, 5 seconds); D648 127 mm x 13 mm x 6,8 mm; D570 3.2 mm x 51 mm Disc 24hr@ 25°C; D792 solid 8 mm x 10 mm Disc; D7867@ 25°C (77°F); D1475.

Internal Data Sources:

[1] FOR90151, [1.1] FOR28964, [2] FOR25158, [3] FOR126256, [4] FOR52239, [5] FOR126257, [6] FOR23912, [7] FOR25148, [8] FOR26823, [9] FOR24553, [10] FOR136400, [11] FOR25155, [12] FOR593777, [13] FOR502534, [14] FOR137858, [15] FOR148057





PRO476™
TOUGH
BLACK



WORKFLOW

Validated workflows need to be followed to achieve properties as provided in the TDS. Examples of validated workflow steps are listed below. Users should defer to the most current workflow information for best results which can be found at <https://www.loctiteam.com/printer-validation-settings>

PRINTER SETTINGS

LOCTITE 3D PRO476 BK is formulated to print optimally on industrial LCD printers. Read the safety data sheet carefully to get details about health and safety instructions. Recommended print parameters:

- Shake resin bottle well before usage
- Temperature: 20°C to 45°C
- Intensity: > 1 mW/cm²

Settings: 405nm at 2.4 mW/cm ²	Measure	Method	Value
Layer Thickness (µm):	µm	Internal	100
Burn-in Region (s)	s	Internal	30
Transition Region (s):	s	Internal	30
Model Region (s):	s	Internal	12

Settings: 385 nm at 5 mW/cm ²	Measure	Method	Value
E _C	mJ/cm ²	Internal	8.24 ^[16]
D _p	mm	Internal	0.17 ^[16]

Settings: 385 nm at 5 mW/cm ²	Measure	Method	Exposure time
D _C = 50µm	s	Internal	1.8*
D _C = 100µm	s	Internal	3.6*

*Exposure times are calculated without a safety factor.

Internal data source:
[16] EOR3395Z





PRO476™
TOUGH
BLACK



WORKFLOW

Validated workflows need to be followed to achieve properties as provided in the TDS. Examples of validated workflow steps are listed below. Users should defer to the most current workflow information for best results which can be found at <https://www.loctiteam.com/printer-validation-settings>

CLEANING

LOCTITE 3D PRO476 BK requires cleaning to achieve specified properties. Prior to post curing, support structures should be removed from the printed part, and the part should then be washed. Use compressed air to remove residual solvent from the surface of the material between intervals.

Post Process Step	Agent	Method	Duration	Intervals	Additional Info
Cleaning	IPA	Ultra sonic bath	2 min	2	Allow parts to dry between intervals
Dry	n.a.	Compressed air	10 to 60 s	2	Air pressure (50psi)
Wait before post curing	n.a.	Ambient condition	60 min	1	Room temperature

POST CURING

LOCTITE 3D PRO476 BK requires post curing to achieve specified properties. It is recommended that either an LED or wide spectrum lamp be used to post cure parts.

UV Curing Unit	UV Source	Intensity	Cure time per side	Additional Settings (Shelf, Output Energy)
Loctite CL36	405nm LED	80 mW/cm ² at 405 nm	15 min	100% top & side, rotary table
Loctite UVALOC 1000	Mercury Arc Bulb (broad spectrum)	30 mW/cm ² at 365 nm	5 min	500 W, lowest shelf
Dymax 5000 EC Flood	Mercury Arc Bulb (broad spectrum)	150 mW/cm ² at 380 nm	10 min	400 W, Shelf K



LOCTITE®

PRO476™

TOUGH
BLACK



WORKFLOW

Validated workflows need to be followed to achieve properties as provided in the TDS. Examples of validated workflow steps are listed below. Users should defer to the most current workflow information for best results which can be found at <https://www.loctiteam.com/printer-validation-settings>

STORAGE

Store **LOCTITE 3D PRO476 BK** in the unopened container in a dry location. Optimal storage: 8°C to 30°C, storage below 8°C or greater than 30°C can adversely affect products properties. More specific information is given in the Safety Data Sheet. Material removed from container may be contaminated during use. For this reason, filter used resin with 190µm mesh filter before placing back into proper storage container.

LIMITATIONS

Vat Printer: **LOCTITE 3D PRO476 BK** is likely possible with recirculation VAT that can handle higher viscosity resins.

LCD printers: **LOCTITE 3D PRO476 BK** can show limited print height for parts with large cross sections.

ADDITIONAL DEVELOPMENT OPTIONS

Colors: **LOCTITE 3D PRO476 BK** formula can be made with additional pigment colors

*These values are calculated without a safety factor.



LOCTITE®

PRO476™ TOUGH



NOTE

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of **Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark Usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.



LOCTITE®



FIND OUT MORE AT
LOCTITEAM.COM

LOCTITE®

Henkel Corporation

loctite3dp@henkel.com



Version 2024/02/02