


STRONG, DURABLE and Rigid Bonds




LOCTITE AA 3961 AND LOCTITE AA 3963 LED LIGHT CURE ADHESIVES provide high strength, durability and rigidity, with fast, tack-free curing. Specially designed for LED curing technology and minimizing cure times, they maximize production efficiency.

**High Strength
& Durability**



**Low
Viscosity**



**LED Curable
(Fast & Tack-Free)**



**Highly
Fluorescent**



To learn more about Henkel's newest light cure innovations
visit www.henkel-adhesives.com

LOCTITE RIGID BONDERS

They have been tested to Henkel's protocols based upon ISO-10993 biocompatibility standards, *with certificates available on request*. These medical device adhesives are ideally suited for the assembly of a variety of devices including, but not limited to:

- Blood collection sets
- Syringes & lancets
- Drug delivery devices
- Anesthesia, epidural & insulin syringes
- Blood oxygenators
- Blood filters
- Heat exchangers
- Blood bowls
- Manifolds
- Blood pressure transducers

TYPICAL SUBSTRATES:

- Stainless Steel, Nitinol, Polycarb, Acrylic, ABS, PP (plasma treated), HDPE (plasma treated).

OTHER COMPATIBLE SUBSTRATES:

- TPE (TPU, Pebax, Hytrel), Plasticized PVC, Thermoset rubber

TYPICAL PROPERTIES[†]

Products	Container size	Appearance [uncured]	Fluorescence [uncured/cured]	Viscosity [mPa-s]	Fixture speed with 405 nm led curing system [secs]	Shear strength on polycarbonate blocks	Needle pullout strength on polycarbonate hubs & 27 gauge ss needle	Shore hardness [shore d]
AA 3961	25 ml Syringe	Clear, colorless	Yes	60	< 5	22.1 N/mm ²	151 N*	71
	1 Liter Bottle							
AA 3963	25 ml Syringe	Clear, colorless	Yes	300	< 5	22.7 N/mm ²	162 N*	72
	1 Liter Bottle							


[†] Estimated values. Please consult the LOCTITE TDS for additional data and details.

* Primarily substrate failure of the SS cannula.



SURFACE TREATMENT:

Polyolefins such as polyethylene (PE) and polypropylene (PP) are often used for disposable medical devices due to their low cost and versatile properties. Since PE and PP are difficult-to-bond plastics, it is common to treat the plastic before assembly to increase the pull strength. Corona, plasma and other pretreatment methods have been shown to increase bond strengths on difficult-to-bond materials when using **LOCTITE AA 3961 or AA 3963**.




CURING

LOCTITE AA 3961 and AA 3963 can be cured with UV or visible light. Henkel's newest LED curing units are ideally suited for rapid curing of select Henkel adhesives. Contact us for more details.



DISPENSING

LOCTITE AA 3961 and AA 3963 can be dispensed manually or with LOCTITE semi-automated and fully automated systems. Contact us for more details.



DETECTION

LOCTITE AA 3961 and AA 3963 contain fluorescent additives allowing for detection in the uncured or cured state. Detection can be accomplished with a simple black light or with vision systems.

REGIONAL HEADQUARTERS

EUROPE, INDIA, MIDDLE EAST, AFRICA

Henkel AG & Co. KGaA
Henkelstraße 67
40589 Düsseldorf
Germany
Tel: +49.211.7970
Tel: +49.211.4008

ASIA-PACIFIC

Henkel (China) Investment Co., Ltd.
Building 7, The Spring Center
No. 99 Jiang Wan Cheng Road
Yang Pu District
Shanghai 200438
China
Tel: +86.21.2891.8000
Tel: +86.21.5509.9552