



Instant Mix™ 1 Minute Epoxy

Description: Loctite Epoxy 1 Minute Instant Mix is a two-part adhesive consisting of an epoxy resin and a hardener. When mixed in equal volumes, the resin and hardener react to produce a tough, rigid, high strength bond, which starts to set in 1 minute and reaches handling strength in 5 to 10 minutes. The static mix nozzle delivers a uniform mixture of resin and hardener every time. It can be used as an adhesive for a wide range of materials or as a versatile filler for gap bonding, surface repairs and laminating. Loctite Epoxy 1 Minute Instant Mix does not shrink and is resistant to water and most common solvents. It can be tinted with earth pigments, cement or sand for color matching and can be sanded and drilled.

Available As:

Item #	Size	Package
1366072	0.47 fl oz (14 ml)	Carded Syringe

Features & Benefits:

- Self-Mixing
- Precise Application
- Sets in 40 to 60 seconds for quick project completion
- Water and Chemical Resistant
- Dries Translucent Yellow
- Machinable
- Does not shrink

Recommended For:

Loctite Instant Mix 1 Minute Epoxy can be used for bonding metal, glass, ceramic, wood, many rigid plastics, china, tile, fiberglass, concrete and stone. Can be combined with fiberglass cloth for a durable patch.

Limitations:

- Not recommended for polyethylene, polypropylene, non-stick coatings, nylon products or flexible materials
- Not suitable for applications requiring short-term heat exposure greater than 302°F (150°C)
- Not recommended for application with prolonged water immersion or continuously wet areas
- Not for use on potable water systems



TECHNICAL DATA SHEET

Typical Uncured Physical Properties:

Color:	Hardener:	Light yellow
	Resin:	Colorless
Base:	Epoxy resin / Polysulfide hardener	
Odor:	Mild amine	
Specific Gravity:	Hardener:	1.12
	Resin:	1.16
Flash Point:	Hardener:	249.8 – 399.2°F (121 - 204°C)
	Resin:	>480°F (249°C)
VOC Content:	CARB	
	Resin & Hardener:	0.1% by weight
Shelf Life:	18 months from date of manufacture (unopened)	
Lot Code Explanation:	YYYY MMXX	
Stamped on front of syringe above the label	YYYY = Year of manufacture MM = Month of manufacture XX = Disregard	
	For example: 2015 1171 Manufactured in November 2015	

Typical Application Properties:

Application Temperature:	Apply between 39°F (4°C) and 95°F (35°C)
Gel Time (5g : 5g):	1 minute*
Handling Time:	5 to 10 minutes*
Full Cure Time:	24 hours*
	*Time is dependent on temperature, humidity and thickness of epoxy applied

Typical Cured Performance Properties:

Color:	Translucent amber	
Cured Form:	Non-flammable solid	
Service Temperature:	-10°F (-23°C) to 120°F (49°C) -10°F (-23°C) to 302°F (150°C)	Long Term (Continuous) Exposure Short Term (Intermittent) Exposure
Water Resistant:	Yes	
Sandable:	Yes	
Paintable:	No but can be tinted using earth pigments, cement or sand	
Tensile Shear Strength:		
Cold Rolled Steel, Sandblasted: 24 hour cure:	2500 psi (17.2 N/mm ²)	

Directions:

Tools Typically Required:

Utility knife, disposable surface (e.g. foil, paper).

Safety Precautions:

Apply and cure in a well-ventilated area. Wear gloves and wash hands after use

Preparation:

Protect work area. Surfaces must be clean, dry and free from oil, wax and paint. Roughen smooth surfaces for better adhesion by sandblasting or sanding with an emery cloth. Wash glass and ceramic surfaces with soap and water then rinse and let dry. Pre-fit parts to be joined. Hold syringe with nozzle end up and pull plunger back slightly allowing air bubbles to rise to top. Snap cap off by pushing to the side (do not twist) and discard. Attach nozzle over syringe opening, push past prongs and turn 90° to lock in place.



TECHNICAL DATA SHEET

Application:

Depress plunger to dispense equal amounts of hardener and resin directly onto surface to be filled or bonded. Remove and discard nozzle. Wipe syringe tip immediately. Retract plunger slightly and close with the cap provided. Place objects together within 40 seconds of adhesive application. Bond sets in 40 to 60 seconds at 68°F (20°C) to 77°F (25°C). Remove any excess adhesive immediately with mineral spirits or rubbing alcohol (follow manufacturer's instructions). Usable strength is obtained within 5 to 10 minutes. Warmer temperatures will shorten the set time and cooler temperatures will lengthen it.

Clean-up:

Remove and discard nozzle. Retract plunger slightly and wipe syringe tip. Remove cap from side holder and place on end of syringe. Clean excess glue immediately by wiping with clean cloth. Acetone may be used to assist in removal. Cured adhesive may be cut away with caution using a sharp blade. Prolonged immersion in paint stripper will soften the cured adhesive to aid removal. Note: Acetone is highly flammable and not compatible with all surfaces. Follow manufacturer's instructions and test on small area before applying.

Storage & Disposal:

Not damaged by freezing. If frozen, warm to room temperature until the resin and hardener become liquid enough to mix. Use an approved hazardous waste facility for disposal.

Label Precautions:

DANGER: Corrosive. Causes eye and skin burns. May cause allergic skin and respiratory reaction. May be harmful if absorbed through skin.

DANGER: Contains epoxy resin, polymercaptopan and amine curing agents. Do not get in eyes or on skin. Do not breathe vapors.

FIRST AID: For eye contact, flush with water for 15 minutes and call a physician. For skin contact, wash thoroughly with soap and water and call a physician if symptoms persist. If swallowed, do not induce vomiting. Call a physician. **KEEP OUT OF THE REACH OF CHILDREN.**

Refer to the Safety Data Sheet (SDS) for further information.

Disclaimer:

The information and recommendations contained herein are based on our research and are believed to be accurate, but no warranty, express or implied, is made or should be inferred. Purchasers should test the products to determine acceptable quality and suitability for their own intended use. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Trusted Performance. Proven Results.

For over 50 years, Loctite Brand adhesives and sealants have taken on the toughest jobs. Used in race cars, airplanes, and even in the space-shuttle, Loctite provides solutions for the most demanding industrial, professional and consumer applications. Loctite gives you not the specialization, power and performance to not only get your job done, but to get it done right.

1-800-624-7767 – Mon-Fri - 9:00a – 4:00p ET

www.loctiteproducts.com

Loctite Brand is part of the Henkel family of brands. Founded in 1876, Henkel is a global leader in the consumer and industrial businesses. Henkel operates worldwide with leading brands and technologies in three business areas: Laundry & Home Care, Beauty Care and Adhesive Technologies.

Henkel Corporation - Professional & Consumer Adhesives Headquarters - Rocky Hill, CT 06067

www.henkelna.com

Revision Date: 08/30/2016 Supercedes: 03/04/2014 Ref. #: 895-331

