

Polycoat RBE FR

Rubberized bitumen emulsion

Tough and flexible vapor proof protective coating with fire classification

CHARACTERISTICS

- ▶ Cold applied
- ▶ Single component, easy to apply
- ▶ Fire resistant - class A
- ▶ Can be applied on damp substrates
- ▶ Can be applied in closed or confined areas
- ▶ Good resistance against chloride and sulphate ions
- ▶ Has good adhesion to most building substrates
- ▶ Seamless/joint free
- ▶ Prevents fungal growth



DESCRIPTION

Polycoat RBE FR is an emulsified rubber modified bitumen coating with fire classification, which dries to form a tough, seamless, flexible vapor proof protective coating.

FIELDS OF APPLICATION

Can be used as vapour / damp proof coating for a wide variety of applications, which includes the following:

- facade cladding system
- damp proof membrane in sandwich constructions
- vapor proof barrier coating for interior & exterior floor & walls

APPLICATION INSTRUCTIONS

The application temperature should be between 5°C to 55°C. Application procedures may vary slightly depending upon site conditions. The general recommended guidelines for the application of the bitumen coating system is as follows:

Surface preparation

The surface shall be cleaned thoroughly of all contaminants like dust, traces of curing compound, oil and grease. Light mechanical grinding/grit blasting/high pressure water jet may be used to clean the surface of all the contaminants depending on the degree of contamination on the surface to be coated. All surface imperfections and protrusions shall be removed and repaired. Structurally unsound and friable concrete must be removed and repaired with a suitable Polycrete* concrete repair mortar.



TDS_Polycoat RBE FR_GCC_0917

1

Priming

In case highly porous substrate, recommended to apply a priming coat prior to the application of the Polycoat RBE FR coating on the substrate. The primer can be prepared in the site by diluting Polycoat RBE FR with 20% water and applying this diluted coat as the primer. For very dry and porous substrates apply two coats of this primer. The primer can be applied to damp or freshly cast concrete surfaces also. However, it should not be applied on waterlogged or flowing water areas. Further coats shall be applied only after the primer coat dries off completely.

Application

Stir the contents of the drum thoroughly before application to remove all sediments. Depending on the dry film thickness required, apply the rubberized bitumen coating @1-4m²/liter/coat. On vertical areas, it is recommended to apply the coating in multiple layers in order to avoid sagging of the heavy bodied coating. Subsequent coats shall be applied only after the previous coat dries off completely and shall be applied at right angles to the previous coat.

COVERAGE

The coverage varies depending on the type substrate. In general, it is recommended to apply at the rate of 4m²/

liter/coat, minimum 2 coats to get thickness of 250 microns DFT on smooth concrete substrate. Coverage may vary on porous / block works.

CLEANING

Clean all tools immediately after use with water. Hardened material can be cleaned with a solvent.

STORAGE & SHELF LIFE

The drums must be stored in a covered area, away from direct sunlight, UV and other sources of heat. The shelf life of the product is up to 12 months if stored as per the recommendations. Excessive exposure to sunlight and UV will result in the deterioration of the product and reduce its shelf life.

HEALTH & SAFETY

As with all bitumen products, caution should always be exercised. Protective clothing such as gloves and goggles should be worn. (See packing for specific instructions). Treat any splashes to the skin or eyes with fresh water immediately. Should any of the products be accidentally swallowed, do not induce vomiting. Call for medical help immediately. Ensure that the container is available for medical attendant to examine any relevant instructions and content details.

SUPPLY

Polycoat RBE FR 20 liter pail & 200 liter drum

TECHNICAL SPECIFICATION

PROPERTIES	VALUES	TEST STANDARDS
Color	dark brown	-
Form	thixotropic viscous liquid	-
Density, [g/cc]	1.08±0.02	ASTM D 2939
Solid content, [%]	45±5 approx	ASTM D 2939
Fire class	class A	ASTM E 84
Initial drying time, [hours]	4 to 6	-
Application temp, [°C]	5 to 55	
Service temp, [°C]	-5 to 75	

All values given are subject to 5-10% variation

Apart from the information given here it is also important to observe the relevant guidelines and regulations of various organisations and trade associations as well as the respective standards. The aforementioned characteristics are based on practical experience and applied testing. Warranted properties and possible uses which go beyond those warranted in this information sheet require our written confirmation. All data given was obtained at an ambient and material temperature of +23°C and 50 % relative air humidity at laboratory conditions unless specified otherwise. Please note that under other climatic conditions hardening can be accelerated or delayed.

The information contained herein, particularly recommendations for the handling and use of our products, is based on our professional experience. As materials and conditions may vary with each intended application, and thus are beyond our sphere of influence, we strongly recommend that in each case sufficient tests are conducted to check the suitability of our products for their intended use. Legal liability cannot be accepted on the basis of the contents of this data sheet or any verbal advice given, unless there is a case of wilful misconduct or gross negligence on our part. This technical data sheet supersedes all previous editions relevant to this product.

