

# CT 722



## VISAGE anti-adhesive agent

### CHARACTERISTICS

- ▶ anti-adhesive agent applied to the silicone matrix during wood structure modeling
- ▶ easy in usage
- ▶ ready to use



### SCOPE OF USE

Ceresit CT 722 Visage should be applied to the silicone matrix to avoid sticking of the matrix to Ceresit CT 720 Visage plaster during wood structure modeling.

### APPLICATION

CT 722 spread out on the silicone matrix as much as needed with a brush or roller, without creating puddles and leaks. While modelling the wood structure, control the quality of the final effect and when needed, regularly apply CT 722 anti-adhesive agent on the matrix.

Lack of anti-adhesive agent or too low amount may result in adhering the matrix to the plaster and in final effect poorer quality of final effect.

### PLEASE NOTE

Work should be carried out at temperatures from +5 °C to +25 °C.

Give adequate ventilation (if necessary use the exhaust) to the spaces in which the work is conducted. Do not allow debris to drain. Avoid inhalation of vapors. Avoid contact with eyes and skin. Do not eat or smoke while working with a mixture. Wash hands after using the product. The measure should not present a hazard under normal conditions of use. In case of contact with skin, wash with soap and water contamination. In case of contact with eyes, rinse thoroughly with water and seek medical advice

### PACKAGING

Plastic canisters 5 l.



CERESIT\_C\_CT722\_TDS\_1\_0116

### TECHNICAL DATA

Base:	mixture of highly refined mineral oils
Density:	0.85 kg/dm <sup>3</sup>
Temperature of use:	from +5 °C to +25 °C
Assumed consumption:	approx. 0.1 l/m <sup>2</sup> of ready made structure of plaster

Shelf life/ Storage: Up to 24 months from date of manufacture. Keep in cool, dry, well ventilated area. Avoid direct solar radiation, heat sources and strong oxidizing agents.

Apart from the information given here it is also important to observe the relevant guidelines and regulations of various organisations and trade associations as well as the respective standards of the German Standards Institute (DIN). The aforementioned characteristics are based on practical experience and applied testing. Warranted properties and possible uses which go beyond those warranted in this information sheet require our written confirmation. All data given was obtained at an ambient and material temperature of +23 °C and 50 % relative air humidity unless specified otherwise. Please note that under other climatic conditions hardening can be accelerated or delayed.

The information contained herein, particularly recommendations for the handling and use of our products, is based on our professional experience. As materials and conditions may vary with each intended application, and thus are beyond our sphere of influence, we strongly recommend that in each case sufficient tests are conducted to check the suitability of our products for their intended use. Legal liability cannot be accepted on the basis of the contents of this data sheet or any verbal advice given, unless there is a case of wilful misconduct or gross negligence on our part. This technical data sheet supersedes all previous editions relevant to this product.



**Henkel CEE**  
Erdbergstrasse 29  
1030 Vienna  
[www.ceresit.com](http://www.ceresit.com)

**Quality for Professionals**