

K 188E



Special Adhesive Extra

For bonding PVC, CV, polyolefin and rubber flooring

CHARACTERISTICS

- ▶ Extra strong tack
- ▶ Suitable for wet, pressure-sensitive and contact bonding
- ▶ Excellent wetting even with difficult coverings
- ▶ Very economical coverage

SCOPE OF USE

Very low-emission, highgrade and highstrength dispersion adhesive for bonding

- PVC flooring, homogeneous and heterogeneous, sheets and tiles
- CV flooring
- quartz vinyl floor tiles
- polyolefin sheeting
- rubber sheets and tiles up to 2.5 mm thickness with a smooth, sanded back
- textile flooring with a latex, PVC or PUR foam backing on absorbent substrates.

Suitable as pressure-sensitive adhesive for bonding PVC and CV floor coverings on impervious, nonabsorbent substrates (e.g. old PVC flooring). Suitable as contact adhesive for bonding coverings on stairs (e.g. moulded rubber steps) or walls (e.g. deflector panels). Ceresit K 188 E meets the highest requirements for indoor air quality and environmental compatibility.

SUBSTRATE PREPARATION

Substrates must comply with the requirements of comparable national standards. In particular, they must be clean, free from structural defects, firm, dry and free of substances which may impair adhesion. After mechanical pretreatment (e.g. grinding/vacuuming), prepare the substrate with suitable Ceresit primers and levelling compounds so that it is ready to receive floor coverings. On mastic asphalt screeds and non absorbent mineral substrates apply a layer of at least 2 mm thickness. Thoroughly clean old, firmly adhering PVC/CV coverings.

APPLICATION

Apply the adhesive evenly to the substrate with a suitable notched trowel. When installing CV or textile floor coverings for residential use, a coarse foam roller may be used alternatively.



CERESIT_C_K188E_TDS_1_0121

Wet bonding (on absorbent substrates):

After a short open time of approx. 10–20 minutes, place the covering material into the still wet adhesive bed, taking care to avoid air pockets, and carefully rub it down to ensure good wetting of the back. The covering material must be free of tension and lie flat on the substrate, otherwise weight it down. Avoid rucking at the joints.

Pressure-sensitive bonding (only for CV and PVC coverings on impervious substrates):

Allow the adhesive to air-dry until it has taken on a uniformly yellowish to transparent colour (approx. 30 – 60 minutes). Then test with a finger to make sure it is touchdry.

Contact bonding:

Apply the adhesive to the back of the floor covering with either roller or A5 notched trowel and to the substrate using an A4 notched trowel. After complete air-drying (finger test!), place the floor covering and rub / roll it down. This method is particularly recommended for bonding rubber and PO materials on impervious substrates.

Always press the ready laid floor covering in place by vigorously rubbing or rolling it down again. Wait at least another 24 hours before welding the joints.

PLEASE NOTE

- Best possible indoor air quality after floor installation work requires conformity to the standard working conditions as well as completely dry substrates, primers and levelling compounds.
- Only carry out floor installation work if the floor temperature is above 15 °C, air temperature above 18 °C and relative humidity below 75 %.
- Remove any skin of dried-up adhesive which may have formed (e.g. due to improper storage). Do not stir in.
- Immediately remove fresh spots of adhesive with a moist cloth.
- Clean tools with soap and water immediately after use.
- Tightly close opened buckets and use them up as soon as possible.
- Open and working time may vary depending on temperature, relative humidity and absorbency of the substrate. They will be shorter at higher temperatures and lower humidity, but longer at lower temperatures, higher humidity and with nonabsorbent substrates.

PRODUCT SAFETY

Ceresit K 188 E is solvent free and a suitable alternative to solvent containing products. The risk of medium or long term release of appreciable concentrations of volatile organic chemicals (VOC) into the ambient air is negligible. Nevertheless ensure good ventilation during and after application and drying. Avoid eating, drinking or smoking while processing this product.

Protect eyes and skin. In case of contact with eyes or skin rinse immediately with plenty of water. After eye contact also seek medical advice.

Information for allergy sufferers on:

Keep out of reach of children.

For professional users.

Apart from the information given here it is also important to observe the relevant guidelines and regulations of various organisations and trade associations as well as the respective standards of the German Standards Institute (DIN). The aforementioned characteristics are based on practical experience and applied testing. Warranted properties and possible uses which go beyond those warranted in this information sheet require our written confirmation. All data given was obtained at an ambient and material temperature of +23 °C and 50 % relative air humidity unless specified otherwise. Please note that under other climatic conditions hardening can be accelerated or delayed.

The information contained herein, particularly recommendations for the handling and use of our products, is based on our professional experience. As materials and conditions may vary with each intended application, and thus are beyond our sphere of influence, we strongly recommend that in each case sufficient tests are conducted to check the suitability of our products for their intended use. Legal liability cannot be accepted on the basis of the contents of this data sheet or any verbal advice given, unless there is a case of wilful misconduct or gross negligence on our part. This technical data sheet supersedes all previous editions relevant to this product.

Safety data sheet available on www.ceresit.com

Ingredients: acrylate copolymer dispersion, modified natural resin, inorganic fillers, poly(1,2-propandiol), wetting agent, thickener, anti-foaming agent, preservative (benzisothiazolinon).

GISCODE D 1 solvent free, according TRGS 610

EMICODE EC 1 very low-emission according to GEV

DISPOSAL

Do not allow product to reach sewage system or any water course. Do not allow to penetrate the ground/ soil. Only recycle totally empty packages. Dispose of hardened product residues as industrial waste similar to household waste or in the container for commercial/ construction site waste. Dispose of unhardened product residues as hazardous waste.

European waste code number (EWC): 08 04 09.

STORAGE

12 months, cool and dry.

PACKAGING

Plastic bucket, 13/20 kg.

TECHNICAL DATA

Supplied as	creamy white, paste	
Open time		
wet bonding	approx. 15 minutes	
pressure-sensitive/ contact bonding	approx. 45 minutes	
Working time		
wet bonding	approx. 40 min for PVC	
pressure-sensitive/ contact bonding	approx. 120 min for PVC	
Load bearing	after approx. 24 hrs	
Curing time (final strength)	after approx. 72 hrs	
Suitability for castor chairs	acc. to DIN EN 12529	
Temperature resistance		
after curing	up to max. 50 °C, can be used on underfloor heating constructions	
for transport	+5 °C to +50 °C, protect against frost	
for storage	+10 °C to +30 °C	

Consumption:

roller	approx. 200 g/m ²	cov. 20 kg/approx. 100 m ²
notch A1	approx. 250 g/m ²	cov. 20 kg/approx. 80 m ²
notch A2	approx. 280 g/m ²	cov. 20 kg/approx. 71 m ²
notch A3	approx. 300 g/m ²	cov. 20 kg/approx. 67 m ²
notch A4	approx. 220 g/m ²	cov. 20 kg/approx. 91 m ²
notch A5	approx. 150 g/m ²	cov. 20 kg/approx. 133 m ²

The above data are based on normal climatic conditions (23 °C / 50 % rel. air humidity). Other climatic conditions can cause a lengthening or shortening of cure and drying times.



Henkel CEE
Erdbergstrasse 29
1030 Vienna
www.ceresit.com

Quality for Professionals