

POLYTHERM AC

Highly efficient, energy-saving flexible coating

Water-based pure acrylic resin proving efficient thermal protection for the entire structure.




CHARACTERISTICS


- ▶ Durable & provides high degree heat insulation properties
- ▶ Very high emittance & reflectance properties
- ▶ Excellent dirt pick-up resistance over longer period of time
- ▶ Reduced thermal conductance and heat gain thereby by increasing energy efficiency
- ▶ Outstanding adhesion over a variety of substrates
- ▶ Waterproofing & resistance to blistering
- ▶ Low VOC & non-toxic
- ▶ UV protection
- ▶ Washable



waterproofing



UV resistant



heat resistant

DESCRIPTION

Polytherm AC is water-based pure acrylic resin proving efficient thermal protection for the entire structure. Polytherm AC is non-toxic, washable & environment friendly forming a seamless membrane that resist many harsh chemicals & bridges hairline cracks. Polytherm AC has high emittance & reflectance as well as a very low conductivity value which reduce thermal shock & heat penetration thereby keeping roofs much cooler in hot summer weather. They offer UV protection & display excellent dirt pick-up resistance and retain their flexibility long after aging.

FIELDS OF APPLICATION

- roofs, terraces, balconies, domes, etc.
- sandwich panels, corrugated sheets
- overcoating on minerals surfaced waterproofing membranes
- concrete facades

APPLICATION INSTRUCTIONS

The application temperature should be between 5°C to 45°C. Application procedures may vary slightly depending upon site conditions. The general recommended guidelines for the application of the coating system is as follows:



TDS_Polytherm AC_RTL_1116

1

Surface preparation

All the surfaces must be cleaned and made free of dust, dirt, moss, oil, grease and other loose particles. This can be achieved by grit/sand/shot blasting. As a minimum, vigorous wire brushing should be employed. All pot holes and surface defects shall be repaired with a suitable concrete repair mortar from the Polycrete* range.

Priming

Polytherm AC does not require priming and can directly be applied onto the surface. In case of highly porous surface, a priming coat is recommended to seal the pores and stabilize the surface. The primer coat can be produced on site by diluting Polytherm AC 1 to 1 with water. Apply the primer coat @ 5m²/L and allow to dry.

Mixing

Polytherm AC is a single component product but mix the contents of the pail thoroughly prior to application to remove any sediment. A slow speed drill and suitable paddle mixer shall be used to avoid the formation of bubbles.

Application

Once mixed, Polytherm AC should be immediately applied either by brush, roller or industrial sprayer. It is recommended that coating be applied in a minimum of

two coats, coating shall be applied 3m²/liter/coat & should not be applied if relative humidity exceeds 95%. Each subsequent coat shall be applied only after the previous coat dries off completely. After application the coating must be back rolled to reduce surface irregularities and improve bonding. Prior to the application of each coat the surface should be examined for signs of pin-holing, etc. To overcoat, it is imperative that the second coat be applied within the specified overcoating time. Note: Do not dilute

COVERAGE

Polytherm AC:	
concrete roof	0.83L/m ² for 500μ DFT
metal roof	0.67L/m ² for 400μ DFT

minimum recommended thickness is 500μ DFT and for metal roof recommended thickness is 400μ DFT this can be achieved in two coats.

CLEANING & DISPOSAL

Clean all equipment & tools using fresh water & flush mineral spirits through spray equipment to prevent rusting. All disposal practices must be in compliance with all local laws and regulations.

STORAGE & SHELF LIFE

Store in a cool, dry place and keep away from all sources of heat and sunlight. In tropical climates, store in air condition rooms. The shelf life is up to 12 months in unopened condition and if stored as per recommendations. Excessive exposure to sunlight, humidity and UV will result in the deterioration of the quality of the product and reduce its shelf life.

SUPPLY

Polytherm AC	20L pail
--------------	----------

*Refer to website for TDS

HEALTH & SAFETY

As with all construction chemical products, caution should always be exercised. Protective clothing such as gloves and goggles should be worn. Treat any splashes to the skin or eyes with fresh water immediately. Should any of the products be accidentally swallowed, do not induce vomiting, but call for medical assistance immediately. For safe handling information on this product, please refer to the Material Safety Data Sheet (MSDS).

Apart from the information given here it is also important to observe the relevant guidelines and regulations of various organisations and trade associations as well as the respective standards. The aforementioned characteristics are based on practical experience and applied testing. Warranted properties and possible uses which go beyond those warranted in this information sheet require our written confirmation. All data given was obtained at an ambient and material temperature of +23°C and 50 % relative air humidity at laboratory conditions unless specified otherwise. Please note that under other climatic conditions hardening can be accelerated or delayed.

The information contained herein, particularly recommendations for the handling and use of our products, is based on our professional experience. As materials and conditions may vary with each intended application, and thus are beyond our sphere of influence, we strongly recommend that in each case sufficient tests are conducted to check the suitability of our products for their intended use. Legal liability cannot be accepted on the basis of the contents of this data sheet or any verbal advice given, unless there is a case of wilful misconduct or gross negligence on our part. This technical data sheet supersedes all previous editions relevant to this product.

TECHNICAL PROPERTIES

PROPERTIES	VALUES	TEST STANDARDS
Drying time (at 25°C & 50% humidity) to set to recoat	45 min	
Solids content, [%]	63±2	ASTMD1644, D2396
Tensile strength, initial, RT (22°C) [Mpa]	1.8	ASTMD2370
Elongation, initial, RT (22°C), [%]	> 200%	ASTMD2370
Tensile strength, G156 1000hrs, RT (22°C), [Mpa]	2.7	ASTMD2370
Elongation, G156 1000hrs, RT (22°C), [%]	> 170%	ASTMD2370
G156, WOM 1,000 hours	Pass	ASTMD4798
Water swelling resistance, [%]	< 8%	ASTMD471
Adhesion (Dry) – concrete, steel & polyurethane form, [PLI]	> 3 PLI*	ASTMC794, D903
Adhesion (wet)- concrete, steel & polyurethane form, [PLI]	> 2 PLI	ASTMC794, D903
Tear resistance, [lbf/in]	> 95	ASTMD624
Water vapor transmission, [perms]	11.6 perms	
Water vapor transmission rate, [g/(h*m ²)]	3.51	
Water vapor transmission [sd (m) Vapordiff equ air thickness]	0.296	
Dirt pick up resistance, [%]	97% (with UV) 71% (without UV)	
Solar reflectivity, [%]	86%	C1549
Emissivity, [%]	90%	C1471
VOC, [g/L]	≤50	ASTMD 3960/ D2369

All values given are subject to 5-10% tolerance

*Applied on concrete and steel with primer



Henkel Polybit Industries Ltd.

PO Box: 293, Umm Al Quwain, UAE

Phone: +971 (6) 76 70 777; Fax: +971 (6) 76 70 197

henkelpolybit@henkel.com; www.henkelpolybit.com

Quality for Professionals