



Potting

Product Name	Description	Key Attributes	Color	Viscosity at 25°C (cP)		Glass Transition Temperature, T _g (°C)	Shore Hardness	Recommended Cure
				Part 1	Part 2			
Two Component								
LOCTITE UK U-09FL	Industrial-grade urethane adhesive	<ul style="list-style-type: none">• Excellent peel strength• Ideal for bonding glass, metal, polycarbonate and other plastics• Provides an ultra-clear, highly flexible bond line that does not yellow	Transparent	7,800	1,100	25.8	45D	5 days at 25°C

Henkel AG & Co. KGaA
Henkelstraße 67
40589 Düsseldorf | Germany

Phone: +1 952 486 6313
E-mail: electronics@henkel.com
www.henkel-adhesives.com/electronics



The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention. The information is protected by copyright. In particular, any reproductions, adaptations, translations, storage and processing in other media, including storage or processing by electronic means, enjoy copyright protection. Any exploitation in whole or in part thereof shall require the prior written consent of Henkel AG & Co. KGaA. Except as otherwise noted, all marks used in this document are trademarks and/or registered trademarks of Henkel and/or its affiliates in the US, Germany, and elsewhere. © Henkel AG & Co. KGaA, 02/2018