



## Replace Glass / Hard Film

### Hard Coating Materials

LOCTITE ABLESTIK 8006NSB

LOCTITE ECCOBOND LM 8895

Properties	Units	LOCTITE ABLESTIK 8006NSB	LOCTITE ECCOBOND LM 8895
Viscosity (cps) Brookfield @ 20 rpm	mPa.s	52,000	12,000
Glass Transition Temperature (T <sub>g</sub> )	°C	158	29
CTE	below	45	26
	above	134	231
Modulus @ RT	N / mm <sup>2</sup>	4,376	4,194
Recommended Cure		2 hrs. @ 160°C / 30 min. @ 175°C	60 min. @ 150°C

Henkel AG & Co. KGaA  
Henkelstraße 67  
40589 Düsseldorf | Germany

Phone: +1 952 486 6313  
E-mail: [electronics@henkel.com](mailto:electronics@henkel.com)  
[www.henkel-adhesives.com/electronics](http://www.henkel-adhesives.com/electronics)



The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention. The information is protected by copyright. In particular, any reproductions, adaptations, translations, storage and processing in other media, including storage or processing by electronic means, enjoy copyright protection. Any exploitation in whole or in part thereof shall require the prior written consent of Henkel AG & Co. KGaA. Except as otherwise noted, all marks used in this document are trademarks and/or registered trademarks of Henkel and/or its affiliates in the US, Germany, and elsewhere. © Henkel AG & Co. KGaA, 02/2018