



# Technical Data Sheet



Technical Data Sheet  
Ref: NRPTX23000TDS  
Issued: 04.09.20  
Number of pages: 3

## Indoor Fill & Repair

### CHARACTERISTICS

- Easy to apply and tool
- Clean up with water
- Over paintable from 1 hour
- Good adhesion to most common household surfaces
- Low odourless
- Solvent-free

### APPLICATION FIELDS

A one-component, ready to use sealant, based on an acrylic dispersion. Ideal for filling indoor connecting joints where some movement is expected prior to painting.

### STANDARDS

- Conforms to EN 15651-1 (CE marking)
- EN 15301-1

Product type F- INT: sealant for facade for interior  
Reaction to fire: Class E



**TECHNICAL DATA:**

| <b>Uncured product</b>   |                                      |                                |
|--------------------------|--------------------------------------|--------------------------------|
| Base:                    | Acrylate dispersion, waterbased      |                                |
| Odour:                   | Characteristic                       |                                |
| Application temperature: | +5°C - +40°C (substrate and ambient) |                                |
| Consistency:             | Non-slump paste                      |                                |
| Density:                 | ~1,61 g/cm <sup>3</sup>              | (ISO 2811-1)                   |
| Resistance to flow:      | ~ 0 mm                               | (ISO 7390)                     |
| Skin formation time:     | ~ 25 minutes                         | (23°C, 50% r.h.)               |
| Curing speed:            | ~ 10 days/5 mm                       | (23°C, 50% r.h., bead 20x10mm) |
| <b>Cured product</b>     |                                      |                                |
| Odour:                   | Odourless                            |                                |
| Shore A hardness:        | ~ 35                                 | (ISO 868)                      |
| 100% Modulus :           | ~ 0,2 N/mm <sup>2</sup>              | (ISO 8339-A)                   |
| Elongation at break:     | ~ 100%                               | (ISO 8339-A)                   |
| Shrinkage:               | ~ -28%                               | (ISO 10563)                    |
| Movement capability:     | 12,5 %                               |                                |
| Recommended joint width: | max. 30 mm                           |                                |
| Service temperature:     | -20°C - +80°C                        |                                |

**INSTRUCTIONS FOR USE****Surface preparation**

All surfaces must be clean, dry and free from contaminants likely to impair adhesion.

**Sealant application**

The sealant should be applied ensuring that the joint is completely filled. Smooth off the sealant with a smoothing tool to ensure good contact between the sealant and the bonding surfaces. Clean up excess sealant with a damp cloth immediately

**Cleaning tools**

Fresh sealant can be cleaned with a cloth dampened with water

Cured sealant can only be removed by mechanical means (e. g. knife or razor blade)

**Please note**

Over paintable from 1 hour dependent on joint width and ambient conditions. Fully cured in 24 hours

**LIMITATIONS.**

Only for use as an interior joint sealant in areas where some movement is expected.

Not recommended for repairing gaps or cracks in walls.

Not suitable for areas of constant immersion or permanent damp (e.g. Aquariums or swimming pools).

Do not use on natural stone (e.g. marble, granite)

This product is not sandable

If in doubt, contact our technical helpline for further assistance



## GENERAL INFORMATION

### Storage

Store in cool dry conditions, protected from frost. Shelf life is 18 months, in the original packaging

### PACKAGING

50ml Tube

100ml Easy Pulse Pack

280ml Cartridge

## HEALTH AND SAFETY

Before using the product please see related Material Safety Data Sheet that is available on request.

“The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. f.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.”

### Henkel Norden AB

Box 151 22

Gustavslundsvägen 151A

SE-167 15 Bromma, Sweden